

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 09-188851

(43)Date of publication of application : 22.07.1997

(51)Int.CI. C09D183/14

(21)Application number : 07-354068 (71)Applicant : TONEN CORP

(22)Date of filing : 29.12.1995 (72)Inventor : TASHIRO YUJI
SUZUKI SUNAO

(54) THERMOSETTING VARNISH

(57)Abstract:

PROBLEM TO BE SOLVED: To obtain a varnish which can give a coating film having heat resistance, adhesion, electrical insulation properties and flexibility by mixing a specified copolysilazane with a solvent.

SOLUTION: Ten (10) pts.wt. copolysilazane having a number-average molecular weight of 500-100,000, comprising structural units represented by formulas I, II and III (wherein R1, R2, R4, R5, R6 and R7 are each an alkyl, an alkenyl, a cycloalkenyl, an aryl, an aralkyl, an alkylamino or an alkylsilyl; and R3 and R8 are each a bivalent aromatic group) in such amounts that the ratio p/q is 0.01-99, and the ratio p/r is 0.01-99 (wherein (p), (q) and (r) are the numbers of moles of the respective kinds of structural units)) is mixed with 1.0-1,000 pts.wt. solvent (e.g. xylene, methyl isobutyl ketone or methyl ethyl ketone). The thermosetting temperature of the copolysilazane is desirably 300°C or above. If the thermosetting temperature needs to be lowered on account of the substrate to be coated, it can be lowered to 200°C by the addition of a crosslinking agent (e.g. tetramethoxysilane) and a metal catalyst (e.g. metal carboxylate).

LEGAL STATUS [Date of request for examination] 28.11.2002

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

